

Samar

7052.01 - 7052.51



Produkt
upholstery

Beschreibung
Gewebemuster

Zusammensetzung
73% recycled polyester FR / 27% polyester FR

Breite
± 140 cm, ± 55 inches

Gewicht
± 663 gr/m¹, ± 21 oz/yd¹

Brandschutzklasse
BS 5852 , Crib 5
Cal TB 117-2013, section 1 , Pass
DIN 4102 , B1
EN 1021/1-2 , Pass
IMO 2010 FTP part 8 , Pass
NF P 92/503-507 , M1
NFPA 260 , Class 1

Reibechtheit
ASTM D3597/D4157 (#10 cotton duck) ,
42.000 double rubs Wyzenbeek
ISO 12947-2 , >50.000 rubs Martindale

Pilling
ASTM D3511
5 (scale 1-5)
ISO 12945-2
4-5 (scale 1-5)

Farbechtheit
AATCC 8
5 (scale 1-5) wet / 5 (scale 1-5) dry
ISO 105 X12
4-5 (scale 1-5) wet / 4-5 (scale 1-5) dry

Lichtehtheit
AATCC 16.2 opt.1 or 16.3 opt. 3
4 (scale 1-5)
ISO 105 B02
6 (scale 1-8)

Schiebewiderstand
ASTM D4034
99 lbf warp / 81 lbf weft
ISO 13936-2
3 mm warp / 2 mm weft

Reißfestigkeit
ASTM D5034
31.6 lbs warp / 60.9 lbs weft

Labels



USCG -
EU MRA
0038



STANDARD
100
507-0023
Hohenstein RTT

Pflege & Instandhaltung



Schrumpfung
Shrinkage 30°
-1.6% warp / -1% weft
Shrinkage 50°
-3% warp / -1.4% weft

Samar

7052.01 - 7052.51

7052.01	7052.02	7052.03	7052.04	7052.05	7052.06	7052.07	7052.08	7052.09
7052.10	7052.11	7052.12	7052.13	7052.14	7052.15	7052.16	7052.17	7052.18
7052.19	7052.20	7052.21	7052.22	7052.23	7052.24	7052.25	7052.26	7052.27
7052.28	7052.29	7052.30	7052.31	7052.32	7052.33	7052.34	7052.35	7052.36
7052.37	7052.38	7052.39	7052.40	7052.41	7052.42	7052.43	7052.44	7052.45
7052.46	7052.47	7052.48	7052.49	7052.50	7052.51			