

Samar

7052.01 - 7052.51



Product

Upholstery

Description

Chequered weave

Composition

73% recycled polyester FR / 27% polyester FR

Width

± 140 cm, ± 55 inches

Weight

± 663 gr/m¹, ± 21 oz/yd¹

Flame retardancy

BS 5852 , Crib 5

Cal TB 117-2013, section 1 , Pass

DIN 4102 , B1

EN 1021/1-2 , Pass

IMO 2010 FTP part 8 , Pass

NF P 92/503-507 , M1

NFPA 260 , Class 1

Abrasion

ASTM D3597/D4157 (#10 cotton duck) ,

42.000 double rubs Wyzenbeek

ISO 12947-2 , >50.000 rubs Martindale

Pilling

ASTM D3511

5 (scale 1-5)

ISO 12945-2

4-5 (scale 1-5)

Colorfastness to crocking

AATCC 8

5 (scale 1-5) wet / 5 (scale 1-5) dry

ISO 105 X12

4-5 (scale 1-5) wet / 4-5 (scale 1-5) dry

Colorfastness to light

AATCC 16.2 opt.1 or 16.3 opt. 3

4 (scale 1-5)

ISO 105 B02

6 (scale 1-8)

Seam slippage

ASTM D4034

99 lbf warp / 81 lbf weft

ISO 13936-2

3 mm warp / 2 mm weft

Breaking strength

ASTM D5034

31.6 lbs warp / 60.9 lbs weft

Labels



USCG -
EU MRA
0038



STANDARD
100
507-0023
Hohenstein RTT

Care & Maintenance



Shrinkage

Shrinkage 30°

-1.6% warp / -1% weft

Shrinkage 50°

-3% warp / -1.4% weft

Samar

7052.01 - 7052.51

7052.01	7052.02	7052.03	7052.04	7052.05	7052.06	7052.07	7052.08	7052.09
7052.10	7052.11	7052.12	7052.13	7052.14	7052.15	7052.16	7052.17	7052.18
7052.19	7052.20	7052.21	7052.22	7052.23	7052.24	7052.25	7052.26	7052.27
7052.28	7052.29	7052.30	7052.31	7052.32	7052.33	7052.34	7052.35	7052.36
7052.37	7052.38	7052.39	7052.40	7052.41	7052.42	7052.43	7052.44	7052.45
7052.46	7052.47	7052.48	7052.49	7052.50	7052.51			